

Article

Numerical Modelling of The Ultrasonic Treatment of Aluminium Melts: An Overview of Recent Advances

Bruno Lebon ^{1,*}, Iakovos Tzanakis ², Koulis Pericleous ³ and Dmitry Eskin ⁴

¹ Brunel Centre for Advanced Solidification Technology, Brunel University London, Kingston Lane, Uxbridge UB8 3PH, UK; Bruno.Lebon@brunel.ac.uk

² Oxford Brookes University, Wheatley Campus, Oxford OX33 1HX, UK; itzanakis@brookes.ac.uk

³ Computational Science and Engineering Group, University of Greenwich, 30 Park Row, London SE10 9LS, UK; K.Pericleous@greenwich.ac.uk

⁴ Brunel Centre for Advanced Solidification Technology, Brunel University London, Kingston Lane, Uxbridge UB8 3PH, UK; Dmitry.Eskin@brunel.ac.uk

* Correspondence: Bruno.Lebon@brunel.ac.uk

Received: 17 September 2019; Accepted: 03 October 2019; Published: date

Abstract: The prediction of the acoustic pressure field and associated streaming is of paramount importance to ultrasonic melt processing. Hence, the last decade has witnessed the emergence of various numerical models for predicting acoustic pressures and velocity fields in liquid metals subject to ultrasonic excitation at large amplitudes. This paper summarizes recent research, arguably the state of the art, and suggests best practice guidelines in acoustic cavitation modelling as applied to aluminium melts. We also present the remaining challenges that are to be addressed to pave the way for a reliable and complete working numerical package that can assist in scaling up this promising technology.

Keywords: numerical modelling; acoustic cavitation; aluminium; ultrasonic melt treatment; non-linear bubble dynamics; sonoprocessing

1. Introduction

Process design has the potential to provide strategic competitive advantage with regards to customer appeal, product cost, and innovation [1,2]. A key element of process innovation involves a fundamental understanding of how materials and process interactions determine manufacturing performance [2].

A continuous mode of production is often more desirable than batch production: advantages of continuous operations include cheaper unit costs of production, energy savings, and homogenization in the quality of the product. However, converting batch processes to continuous modes is not straight-forward [3]. In the past 6 years, the authors have been researching how to upscale the promising technology of ultrasonic melt processing by moving applications from batch mode to inline mode [4].

Ultrasonic melt processing (USP) is an effective method for degassing, filtration, and grain refinement of light metal alloys on the industrial scale [5–7]. The beneficial effects of USP are attributed to acoustic cavitation: the violent pulsation and collapse of gas bubbles under the influence of a strong acoustic pressure field [8,9], and acoustic streaming: the fluid motion that results from the attenuation of the acoustic pressure wave as it propagates in the liquid [10]. While USP works well in batch degassing or grain refining of a single cast billet or ingot in direct-chill (DC) casting [11], it does not scale up very well for continuous processing, unless multiple ultrasound sources are used [4]. Current research is now focusing on upscaling this promising technology and achieving high

efficiency when treating large melt volumes in continuous mode and with a minimum number of ultrasound sources.

To optimize USP, recirculation patterns and mass exchanges between the cavitation zone and the rest of the liquid bulk need to be adequately quantified. In addition, melt recirculation reduces temperature gradients and promotes a preferred equiaxed grain structure [12]. In DC casting, acoustic streaming improves chemical homogeneity and promotes grain refinement through deagglomeration of clusters, wetting of inclusions, dispersion of substrates, and solid phase fragmentation [7,13,14]. However, it is challenging to visualize acoustic streaming in liquid aluminium due to its opaqueness and high operating temperature. Therefore, studies of acoustic streaming must include modelling in conjunction with X-ray imaging [15–18] to predict the generation of cavitation bubbles, their transport, and acoustic propagation in the presence of attenuation.

A recent review of acoustic pressure modelling presents the challenges facing acoustic cavitation modelling [19] and has been the starting point for the model that resulted from a joint collaboration between Brunel and Greenwich universities in the U.K. [4]. Since then, a novel ‘advanced’ model that incorporates acoustic streaming with cavitation dynamics has been made available [20], enabling more accurate predictions of processing simulations involving cavitation bubbles at an affordable computational cost. This recent progress is summarized in this overview giving readers a good starting point in ultrasonic process modelling.

2. Existing models

2.1. Acoustic Cavitation Model

The theory is reproduced here as a comprehensive summary of acoustic cavitation treatment in modelling of ultrasonic melt processing. The starting point of acoustic cavitation modelling is the Caflisch equations [21]. Sound propagation in a liquid containing bubbles has been studied with a set of nonlinear equations postulated by van Wijngaarden in the 1960s [22], and then derived mathematically by Caflisch *et al.* [21] using Foldy’s method [23]:

$$\frac{\partial p}{\partial t} + \rho_l c_l^2 \nabla \cdot \mathbf{u} = \rho_l c_l^2 \frac{\partial \phi}{\partial t}, \text{ and} \quad (1)$$

$$\rho_l \frac{\partial \mathbf{u}}{\partial t} + \nabla p = \mathbf{F}, \quad (2)$$

where p is the acoustic pressure, \mathbf{u} are the velocities, ρ_l is the (pure) liquid density, c_l is the speed of sound in pure liquid, $\phi = VN = \frac{4}{3}\pi NR^3$ is the bubble phase fraction for a bubbly system with a bubble density of N and consisting of identical bubbles each of radius R . V denotes the volume of a single bubble. The bubble density is assumed to be given by a step function

$$N = \begin{cases} N_0 & \text{if } |P| > P_B \\ 0 & \text{if } |P| \leq P_B \end{cases} \quad (3)$$

where $P_B = 1 + \sqrt{\frac{4}{27} \frac{S^3}{1+S}}$ is the Blake threshold [24,25], with the dimensionless Laplace tension $S = \frac{2\sigma}{p_0 R_0}$, σ is the surface tension between the liquid and gas, p_0 is the atmospheric pressure, and R_0 is the equilibrium radius of the bubbles. The momentum source term \mathbf{F} can be used to prescribe acoustic velocity sources, e.g. due to the vibrating horn.

The radius of a bubble is obtained by solving a second order ordinary differential equation (ODE). For an accurate bubble dynamics representation at high forcing pressures, compressibility has to be taken into account. For liquid metals, bubble dynamics can be represented by the Keller–Miksis equation [26]

$$\rho_l \left[\left(1 - \frac{\dot{R}}{c_l}\right) R \ddot{R} + \frac{3}{2} \left(1 - \frac{\dot{R}}{3c_l}\right) \dot{R}^2 \right] = \left(1 + \frac{\dot{R}}{c_l} + \frac{R}{c_l} \frac{d}{dt}\right) \left[p_g + p_v - \frac{2\sigma}{R} - \frac{4\mu_l \dot{R}}{R} - p_0 \{1 - A \sin(\omega t)\} \right], \quad (4)$$

where p_v is the vapour pressure of the gas in the bubble, μ_l is the dynamic viscosity of the pure liquid, A is the normalized pressure amplitude (relative to p_0), and ω is the angular frequency of the ultrasonic source. Taking into account the effect of heat transfer during bubble dynamics [27,28], the gas pressure p_g is evaluated by solving the following ODE:

$$\frac{dp_g}{dt} = \frac{3}{R} \left[(\gamma - 1)k \frac{dT}{dr} \Big|_{r=R} - \gamma p_g \dot{R} \right], \quad (5)$$

where k is the thermal conductivity of the bubble gas, T is the temperature inside the bubble, and γ is the polytropic exponent. When assuming adiabatic bubble pulsation, the polytropic exponent is given by $\gamma = 1.4$. The temperature gradient at the bubble surface is approximated linearly following the method of Toegel *et al.* in water [29]

$$\frac{dT}{dr} \Big|_{r=R} = \frac{T - T_\infty}{\sqrt{(RD)/\{3(\gamma - 1)\dot{R}\}}}, \quad (6)$$

where T_∞ is the liquid bulk temperature and D is the gas diffusivity. The bubble temperature is solved for by using another ODE expressing the first law of thermodynamics

$$c_v \dot{T} = 4\pi R^2 k \frac{T - T_\infty}{l_{th}} - p_g \dot{V}, \quad (7)$$

where the thermal diffusion length $l_{th} = \min\left(\frac{R}{\pi}, \sqrt{\frac{RD}{R}}\right)$ and c_v is the specific heat capacity of the gas.

Solving the Caflisch equations coupled with the above ODEs is very computationally intensive. In general, the acoustic pressure p is required to compute the momentum source term that corresponds to acoustic streaming. To optimize the computational procedure and reduce its time cost, the following approximation is used in recent works.

$\Re(Pe^{i\omega t})$ denotes the harmonic part of the acoustic pressure p . A nonlinear extension [25,30] of the linear Helmholtz equation originally derived by Commander and Prosperetti [31] from the Caflisch equations approximately describes the complex amplitude P as

$$\nabla^2 P + K^2 P = 0. \quad (8)$$

Commander and Prosperetti defined the complex wave number K using

$$K^2 = \frac{\omega^2}{c_l^2} \left(1 + \frac{4\pi c_l^2 N R_0}{\omega_0^2 - \omega^2 + 2jb\omega} \right). \quad (9)$$

where ω_0 is the resonant frequency of the bubbles, j is the complex number satisfying $j^2 = -1$, and b is the damping factor defined elsewhere [31]. Louisnard [25] generalized this linear model while keeping realistic values for dissipation of energy in inertial cavitation, resulting in a nonlinear model. However, this model suffers from two deficiencies: 1) the real part of K^2 was taken to approach that of Commander and Prosperetti, and 2) the Helmholtz equation used by the model comes from the linear theory. To address these issues, the real and imaginary parts of the coefficient K^2 have been rigorously re-derived by Trujillo [30] as

$$\Re(K^2) = \frac{\omega^2}{c_l^2} - \frac{\mathcal{A}}{|P|}, \quad \text{and} \quad (10)$$

$$\Im(K^2) = -\frac{\mathcal{B}}{|P|}, \quad (11)$$

where

$$\mathcal{A} = -\frac{\rho_l \omega^2}{\pi} \int_0^{2\pi} \frac{\partial^2 \phi}{\partial \tau^2} \cos\left(\tau + \frac{\pi}{2}\right) d\tau, \quad (12)$$

$$\mathcal{B} = \frac{\rho_l \omega^2}{\pi} \int_0^{2\pi} \frac{\partial^2 \phi}{\partial \tau^2} \sin\left(\tau + \frac{\pi}{2}\right) d\tau, \quad \text{or} \quad (13)$$

$$\mathcal{A} = -\frac{\rho_l \omega^2}{\pi} \int_0^{2\pi} \frac{\partial \phi}{\partial \tau} \sin\left(\tau + \frac{\pi}{2}\right) d\tau, \quad (14)$$

$$\mathcal{B} = -\frac{\rho_l \omega^2}{\pi} \int_0^{2\pi} \frac{\partial \phi}{\partial \tau} \cos\left(\tau + \frac{\pi}{2}\right) d\tau, \quad (15)$$

where the non-dimensional time τ is within one period, i.e. $[0, 2\pi]$. The boundary conditions for the nonlinear Helmholtz equation are generally defined as:

- $\nabla P \cdot \mathbf{n} = 0$ for infinitely hard boundaries (such as crucible walls),
- $P = AP_0$ at the surface of the sonotrode, and
- Setting $P = 0$ in the cell layer above the liquid level to approximate the π phase shift that occurs upon reflection from the free surface [32].

This nonlinear Helmholtz equation is rather simple to solve using the Finite Element Method (FEM), thereby facilitating the numerical evaluation of the acoustic field in the presence of cavitation bubbles [19,20,25,30] in commercial packages such as COMSOL Multiphysics. Solution of this equation using the Finite Volume Method (FVM) is trickier and requires special preconditioning [32]; however, the flow equations are simpler to solve in the FVM framework.

2.2. Macroscopic Flow Model

Acoustic streaming models in the literature generally follow the work of Eckart [33] by incorporating the streaming force \mathbf{f} as

$$\mathbf{f} = -\nabla(\rho_l \overline{\mathbf{v} \otimes \mathbf{v}}), \quad (16)$$

(where \mathbf{v} is the acoustic velocity) to the continuity and momentum conservation equations, leading to

$$0 = \nabla \cdot (\rho_l \mathbf{u}) + \nabla \cdot (\overline{\rho_v \mathbf{v}}), \quad (17)$$

$$0 = \mathbf{f} - \nabla p + \mu_l \nabla^2 \mathbf{u}, \quad (18)$$

where ρ_v is the density variation that is caused by the primary acoustic field. However, equation (18) is the momentum equation of a creeping flow driven by the acoustic streaming and is therefore applicable to Reynolds numbers much smaller than 1 [20]. Since acoustic cavitation processes would involve much larger Reynolds numbers, the streaming velocity should instead be calculated from a full steady state Navier–Stokes equation [34]

$$\nabla(\rho_l \mathbf{u} \otimes \mathbf{u}) = \mathbf{f} - \nabla p + \mu_l \nabla^2 \mathbf{u}. \quad (19)$$

However, the solution of equation (19) is difficult since the streaming flow observed experimentally is turbulent [35] and resolving small-scale eddies with the Navier–Stokes equation is not trivial [20]. Instead of solving for streaming directly, the latest papers follow the approach of Louisnard [20] by computing the streaming force from the solution of the nonlinear Helmholtz equation (8) and injecting the result into the momentum equation. This approach has been validated in recent works describing acoustic streaming [20,35–37] and has also been applied to DC casting [38].

3. Numerical Simulations of the Acoustic Field in Crucibles, Moulds and Launderers

There is a dearth of contributions in the literature regarding the specific modelling of ultrasonic melt processing. This is not surprising since accurate measurements of acoustic pressures in aluminium have only recently been made available [39,40]. Some of the first modelling contributions are those of Nastac [41–43] who presented two approaches for modelling grain refinement of an A356 alloy. A similar approach is followed by other authors to model nanoparticle dispersion [44] and the distribution of acoustic pressure in a launder [45]. The first method consists of solving the RANS equations using a classical hydrodynamic cavitation model [46] that is implemented in commercial CFD packages. The essence of this method can be summarized as follows. The liquid–bubble mass transfer is governed by a bubble transport equation in the following form

$$\frac{D(\rho_b \phi)}{Dt} = R_G - R_C, \quad (20)$$

where ρ_b is the bubble density, and the source terms R_G and R_C account for bubble growth and collapse, respectively. These source terms are calculated using the growth of a single spherical bubble based on a bubble dynamics model (e.g. Rayleigh–Plesset [47], Keller–Miksis [26], Neppiras–Noltingk [48]). This equation is coupled with the flow conservation equations, together with a suitable closure for turbulence. However, as beautifully presented by Louisnard [20], this model is restricted to bubbly liquids containing vapour bubbles only. With the vapour pressure of aluminium at the melting point being negligible [49], it is unlikely that aluminium vapour bubbles would form in the melt bulk [50] with gas, hydrogen-filled bubbles, forming instead. This therefore prohibits the use of any hydrodynamic cavitation models for the inertial acoustic cavitation bubbles that are present in liquid aluminium treatment.

The second approach in Nastac’s contribution is, however, more appropriate and is a precursor to the method highlighted in this overview. In this indirect method, the acoustic field is solved for by using a linear Helmholtz equation, closed with the Neppiras–Noltingk model [48]. However, as argued in the previous section, this method suffers from various deficiencies: the linear Helmholtz model is inadequate in the presence of cavitation bubbles, since pressure propagation is nonlinear in this regime. The Neppiras–Noltingk model does not account for acoustic radiation, which is crucial at high forcing pressures. Other authors also used a linear acoustic propagation model to study the treatment of AlSi7Mg alloy melt in sand casting, even though pressures larger than 2 MPa have been predicted [51]. A linear model was also employed to compute the acoustic pressure field in a SCN-1 wt% camphor alloy, which is often used as a transparent analogue to aluminium melt [13,52].

Another attempt to obtain an accurate prediction of the acoustic pressure field was through the solution of the Cafilisch equations (1–2) [38]. In this approach, Lebon *et al.* directly computed the acoustic field using the nonlinear equations governing sound propagation in bubble liquids [21,53,54] and validated the model using experimental data from the literature, as shown in Figure 1.




Figure 1. Validation of Cafilisch approach to computing acoustic pressures [54] using experimental data from Campos-Pozuelo et al. [10].

Adequate pressures were predicted as compared with the measurements using a calibrated cavimeter [39,40] enabling the extension of the model to account for nanoparticle deagglomeration [55], fragmentation of dendrites [56], the erosion of thermally-sprayed splats [57], or contactless

ultrasound due to Lorentz forces from an electromagnetic coil [58]. However, this method suffers from various drawbacks. A bubble dynamics ODE must be solved in each computational cell of the domain, with the use of an adaptive time stepping scheme to stabilize the solution procedure for each computational cell. The method is also prone to numerical diffusion and requires the use of high-order discretization schemes in space and time, and a special staggering scheme [59]. These issues prohibit the application of the model to complex 3D geometries due to the extreme computational requirements.

More recently, nonlinear models of pressure propagation have been used in the context of melt processing. Nonlinear models are required to more adequately capture the attenuation of pressure due to the presence of cavitating bubbles, as shown in Figure 2. Huang *et al.* [60] used an improved nonlinear Helmholtz model [61] to predict the cavitation depth in sonication of an Al-Cu melt. Lebon *et al.* used Louisnard's model to compute acoustic pressures in water and aluminium vessels [35]. This model was adapted and improved to model acoustic pressures in DC casting [38]. The same approach has also been used by Yamamoto and Komarov [37]. The last two studies are conducted in conjunction with acoustic streaming and are discussed in the next section.




Figure 2. Difference in predicted acoustic pressures between linear and nonlinear models. The nonlinear model includes the attenuating effect of cavitating bubbles below the sonotrode. The dash-dotted line denotes the Blake threshold for hydrogen bubbles in aluminium, with $R_0 = 3 \mu\text{m}$.

4. Effect of Acoustic Streaming

The numerical study of acoustic streaming in melt processing is even sparser in the literature. A prediction of ultrasonic DC clad casting using the Navier–Stokes equations only has been recently published [62]. Acoustic streaming is implemented by a direct solution of the sonotrode motion in ANSYS Fluent and applying the transient effects in steady state equations, although the implementation details of the process are not described. The model does not include the effect of cavitation bubbles, so acoustic shielding is not considered. As reported in [63], this method does not appear to capture the flow reversal observed at certain irradiation powers.

Other significant contributions, however, employ acoustic streaming models computing the acoustic streaming force as per equation (16). Simulation of convective flow for an Al-2% Cu alloy has been performed by Wang *et al.* [12,64,65] using the Lighthill approach [34]. This approach predicts a fast velocity jet below the sonotrode, and comparison with a corresponding experiment reveals that the fast streaming flattens the temperature gradient and promotes an equiaxed grain structure. Another approach involved the use of the Ffowcs Williams and Hawkings (FW–H) equation generally used to compute the propagation of aerodynamic noise to model the acoustic pressure in Fluent [66,67]. Another commercial CFD software package, Flow3D, has been used to model acoustic streaming during the treatment of an A356 alloy melt without detailing the modelling procedure [68].

Inspired by Louisnard's nonlinear model coupled with acoustic streaming, Lebon *et al.* [35] validated an acoustic streaming model using results from a Particle Image Velocimetry (PIV) experiment using a TSI system [63], as shown in Figure 3. While the model offers only qualitative agreement with the experiment, this progress is encouraging because:

1. Despite simulating the problem in two dimensions, the correct order of magnitude of acoustic streaming is recovered.
2. The net flow reversal below the sonotrode observed at low operating powers is predicted by the model.
3. The comparison holds for a time-averaged analysis of transient results, which mimics the way velocities are recorded by PIV.
4. The model is tractable since the Helmholtz equation is easier to solve than a system of ODEs representing bubble dynamics.




Figure 3. Comparison between measured velocities using Particle Image Velocimetry (PIV) [63] in water and predictions of acoustic streaming using the numerical model described in [35]. The velocities are in m s^{-1} . The grey bar at the top of each contour represents the vibrating surface. The dataset used to reproduce these results is available elsewhere [69].

However, a remaining challenge is the suitable choice of the bubble number density as a parameter for the simulation. This study of acoustic streaming in water revealed that the predicted flow field is sensitive to the assumed bubble volume fraction, and therefore of bubble density by extension. The bubble density can also vary spatially, although a step function such as the one described by equation (3) helps in limiting the presence of bubbles in regions below the Blake threshold. Semi-empirical values in the range 10^9 – 10^{12} m^{-3} have been reported to lead to acceptable results [32,35,54,70–72]. Aside the difficulties in choosing the appropriate bubble density for a particular simulation, variation in bubble density due to differences in melt quality, presence of impurities and agglomerates, or variation in degassing times presents further challenges.

This model was further improved using Trujillo's mathematically rigorous derivation of the complex wavenumber (9) and was then applied to DC casting using a continuum model [38]. Figure 4 shows the results of a numerical model of ultrasonic processing in DC casting. The predicted sump profile is altered by the fast streaming jet of hot liquid aluminium down the axis of the billet, thereby shortening the transition region at the centre of the billet. Observed grain orientations at the centre of cast billets confirm this prediction [38]. The model also predicts a slightly increased rate of porosity defects at the centre of billet cast with ultrasonic processing, as shown by the increased Niyama criterion at the centre of the domain (Figure 5). However, any experimental observation of increased porosity has not been reported so far.




Figure 4. Comparison of sump profiles between conventional DC casting (left) and ultrasonic assisted DC casting (right). f_s is the solid fraction using the casting conditions defined in [38]. Arrows are shown for the scale of the velocity field. The red dash-dotted line represents the liquidus temperature and the blue dash-dotted line denotes the coherency temperature (solid packing fraction). The dataset used to reproduce these results is available elsewhere [73].




Figure 5. Comparison using the Niyama criterion between conventional DC casting (left) and ultrasonically assisted DC casting (right) using the casting conditions defined in [38]. The larger values upon sonication indicate an increased probability of porosity defects at the centre of the cast billet.

Another research group independently used the same acoustic pressure formulation: Yamamoto and Komarov applied a similar model to aluminium [37] to reveal that attenuation of ultrasound and wave numbers are larger in the molten aluminium than in water, and that acoustic streaming flow is slower in the aluminium melt as compared with water. This is in agreement with our experimental study in [40] where shielding and acoustic damping were found to be more pronounced in liquid aluminium compare to water, obstructing the wave propagation into the bulk.

5. Current Challenges and Future Outlook

This summary has highlighted the requirement of considering the appropriate physics when modelling the complex phenomenon of ultrasonic melt treatment. However, more effort is required for an accurate prediction of actual treatment conditions. Aside from a recent contribution studying resonance in crucibles [58], the boundary conditions used in the models encountered in USP modelling so far are basic and do not take into account the vibration of the solid walls of a sonoreactor or reflection off real, rough crucible walls. Crevices in the walls could also act as seeds for nucleating bubbles and these are not taken into account by any model encountered so far. This is crucial in situations where resonance is required and both the changing bubbly media and imperfect container walls affect the resonant frequency of the system [58,74].

The stability of the heat balance solver upon mesh deformation and solidification front motion is still an issue for accurate modelling of ultrasonic processing in the presence of solidification. This limits the accuracy of casting simulations and need to be addressed for more accurate sump profile predictions. There is also an uncertainty on the effect of the entrained cavitating bubbles and acoustic streaming jet on the packing fraction in the semi-solid region of a casting domain, and therefore on the delimitation between slurry and mushy zones. These need to be quantified accurately for more reliable predictions.

Since acoustic streaming modifies the grain morphology of the billet, the coherency temperature is expected to vary locally in the sump. Further study is required to determine the dependency of this parameter on the flow. However, an accurate *a priori* prediction is rendered difficult since the knowledge of the grain size and morphology is required before choosing the correct solid packing fraction.

Author Contributions: conceptualization, B.L., I.T., K.P. and D.E.; methodology, B.L. and I.T.; software, B.L.; validation, B.L. and I.T.; formal analysis, B.L. and I.T.; investigation, B.L. and I.T.; resources, B.L. and I.T.; data curation, B.L. and I.T.; writing—original draft preparation, B.L.; writing—review and editing, B.L., I.T., K.P. and D.E.; visualization, B.L. and I.T.; supervision, K.P. and D.E.; project administration, I.T., K.P. and D.E.; funding acquisition, I.T., K.P. and D.E.

Funding: This research was funded by the Engineering and Physical Sciences Research Council (EPSRC), UK, grant numbers EP/N007638/1, EP/R011001/1, EP/R011044/1 and EP/R011095/1.

Conflicts of interest: The authors declare no conflict of interest.

References

1. Hill, M. Product and process design for structured products. *AIChE Journal* **2004**, *50*, 1656–1661.
2. Kowalski, A.J.; Cooke, M.; Hall, S. Expression for turbulent power draw of an in-line Silverson high shear mixer. *Chemical Engineering Science* **2011**, *66*, 241–249.
3. Håkansson, A. Rotor-Stator Mixers: From Batch to Continuous Mode of Operation—A Review. *Processes* **2018**, *6*, 32.
4. Eskin, D.G.; Tzanakis, I.; Wang, F.; Lebon, G.S.B.; Subroto, T.; Pericleous, K.; Mi, J. Fundamental studies of ultrasonic melt processing. *Ultrasonics Sonochemistry* **2019**, *52*, 455–467.
5. Abramov, O.V. Action of high intensity ultrasound on solidifying metal. *Ultrasonics* **1987**, *25*, 73–82.
6. Campbell, J. Effects of vibration during solidification. *International Metals Reviews* **1981**, *26*, 71–108.
7. Eskin, G.I.; Eskin, D.G. *Ultrasonic treatment of light alloy melts*; Second edition.; Taylor & Francis, CRC Press: Boca Raton, 2015; ISBN 978-1-4665-7798-5.
8. Neppiras, E.A. Acoustic cavitation. *Physics Reports* **1980**, *61*, 159–251.
9. Tzanakis, I.; Eskin, D.G.; Georgoulas, A.; Fytanidis, D.K. Incubation pit analysis and calculation of the hydrodynamic impact pressure from the implosion of an acoustic cavitation bubble. *Ultrasonics Sonochemistry* **2014**, *21*, 866–878.
10. Campos-Pozuelo, C.; Granger, C.; Vanhille, C.; Moussatov, A.; Dubus, B. Experimental and theoretical investigation of the mean acoustic pressure in the cavitation field. *Ultrasonics Sonochemistry* **2005**, *12*, 79–84.
11. Eskin, D.G. *Physical Metallurgy of Direct Chill Casting of Aluminum Alloys*; 0 ed.; CRC Press, 2008; ISBN 978-0-429-14523-0.

12. Wang, G.; Croaker, P.; Dargusch, M.; McGuckin, D.; StJohn, D. Simulation of convective flow and thermal conditions during ultrasonic treatment of an Al-2Cu alloy. *Computational Materials Science* **2017**, *134*, 116–125.
13. Shu, D.; Sun, B.; Mi, J.; Grant, P.S. A High-Speed Imaging and Modeling Study of Dendrite Fragmentation Caused by Ultrasonic Cavitation. *Metallurgical and Materials Transactions A* **2012**, *43*, 3755–3766.
14. Tzanakis, I.; Xu, W.W.; Eskin, D.G.; Lee, P.D.; Kotsovinos, N. In situ observation and analysis of ultrasonic capillary effect in molten aluminium. *Ultrasonics Sonochemistry* **2015**, *27*, 72–80.
15. Tzanakis, I.; Xu, W.W.; Lebon, G.S.B.; Eskin, D.G.; Pericleous, K.; Lee, P.D. In Situ Synchrotron Radiography and Spectrum Analysis of Transient Cavitation Bubbles in Molten Aluminium Alloy. *Physics Procedia* **2015**, *70*, 841–845.
16. Xu, W.W.; Tzanakis, I.; Srirangam, P.; Mirihanage, W.U.; Eskin, D.G.; Bodey, A.J.; Lee, P.D. Synchrotron quantification of ultrasound cavitation and bubble dynamics in Al-10Cu melts. *Ultrasonics Sonochemistry* **2016**, *31*, 355–361.
17. Wang, F.; Eskin, D.; Mi, J.; Wang, C.; Koe, B.; King, A.; Reinhard, C.; Connolley, T. A synchrotron X-radiography study of the fragmentation and refinement of primary intermetallic particles in an Al-35 Cu alloy induced by ultrasonic melt processing. *Acta Materialia* **2017**, *141*, 142–153.
18. Wang, B.; Tan, D.; Lee, T.L.; Khong, J.C.; Wang, F.; Eskin, D.; Connolley, T.; Fezzaa, K.; Mi, J. Ultrafast synchrotron X-ray imaging studies of microstructure fragmentation in solidification under ultrasound. *Acta Materialia* **2018**, *144*, 505–515.
19. Tudela, I.; Sáez, V.; Esclapez, M.D.; Díez-García, M.I.; Bonete, P.; González-García, J. Simulation of the spatial distribution of the acoustic pressure in sonochemical reactors with numerical methods: A review. *Ultrasonics Sonochemistry* **2014**, *21*, 909–919.
20. Louisnard, O. A viable method to predict acoustic streaming in presence of cavitation. *Ultrasonics Sonochemistry* **2017**, *35*, 518–524.
21. Caflisch, R.E.; Miksis, M.J.; Papanicolaou, G.C.; Ting, L. Effective equations for wave propagation in bubbly liquids. *Journal of Fluid Mechanics* **1985**, *153*, 259.
22. Wijngaarden, L.V. On the equations of motion for mixtures of liquid and gas bubbles. *Journal of Fluid Mechanics* **1968**, *33*, 465.
23. Foldy, L.L. The Multiple Scattering of Waves. I. General Theory of Isotropic Scattering by Randomly Distributed Scatterers. *Physical Review* **1945**, *67*, 107–119.
24. Atchley, A.A. The Blake threshold of a cavitation nucleus having a radius-dependent surface tension. *The Journal of the Acoustical Society of America* **1989**, *85*.
25. Louisnard, O. A simple model of ultrasound propagation in a cavitating liquid. Part I: Theory, nonlinear attenuation and traveling wave generation. *Ultrasonics Sonochemistry* **2012**, *19*, 56–65.
26. Keller, J.B.; Miksis, M. Bubble oscillations of large amplitude. *The Journal of the Acoustical Society of America* **1980**, *68*, 628–633.
27. Jamshidi, R.; Brenner, G. Dissipation of ultrasonic wave propagation in bubbly liquids considering the effect of compressibility to the first order of acoustical Mach number. *Ultrasonics* **2013**, *53*, 842–848.
28. Gadi Man, Y.A.; Trujillo, F.J. A new pressure formulation for gas-compressibility dampening in bubble dynamics models. *Ultrasonics Sonochemistry* **2016**, *32*, 247–257.
29. Toegel, R.; Gompf, B.; Pecha, R.; Lohse, D. Does Water Vapor Prevent Upscaling Sonoluminescence? *Physical Review Letters* **2000**, *85*, 3165–3168.
30. Trujillo, F.J. A strict formulation of a nonlinear Helmholtz equation for the propagation of sound in bubbly liquids. Part I: Theory and validation at low acoustic pressure amplitudes. *Ultrasonics Sonochemistry* **2018**, *47*, 75–98.
31. Commander, K.W.; Prosperetti, A. Linear pressure waves in bubbly liquids: Comparison between theory and experiments. *The Journal of the Acoustical Society of America* **1989**, *85*, 732–746.
32. Lebon, G.S.B.; Tzanakis, I.; Pericleous, K.; Eskin, D. Experimental and numerical investigation of acoustic pressures in different liquids. *Ultrasonics Sonochemistry* **2018**, *42*, 411–421.
33. Eckart, C. Vortices and Streams Caused by Sound Waves. *Physical Review* **1948**, *73*, 68–76.
34. Zarembo, L.K. Acoustic Streaming. In *High-Intensity Ultrasonic Fields*; Rozenberg, L.D., Ed.; Springer US: Boston, MA, 1971; pp. 135–199 ISBN 978-1-4757-5410-0.

35. Lebon, G.S.B.; Tzanakis, I.; Pericleous, K.; Eskin, D.; Grant, P.S. Ultrasonic liquid metal processing: The essential role of cavitation bubbles in controlling acoustic streaming. *Ultrasonics Sonochemistry* **2019**, *55*, 243–255.
36. Fang, Y.; Yamamoto, T.; Komarov, S. Cavitation and acoustic streaming generated by different sonotrode tips. *Ultrasonics Sonochemistry* **2018**, *48*, 79–87.
37. Yamamoto, T.; Komarov, S. Investigation on Acoustic Streaming During Ultrasonic Irradiation in Aluminum Melts. In *Light Metals 2019*; Chesonis, C., Ed.; Springer International Publishing: Cham, 2019; pp. 1527–1531 ISBN 978-3-030-05863-0.
38. Lebon, G.S.B.; Salloum-Abou-Jaoude, G.; Eskin, D.; Tzanakis, I.; Pericleous, K.; Jarry, P. Numerical modelling of acoustic streaming during the ultrasonic melt treatment of direct-chill (DC) casting. *Ultrasonics Sonochemistry* **2019**, *54*, 171–182.
39. Tzanakis, I.; Hodnett, M.; Lebon, G.S.B.; Dezhkunov, N.; Eskin, D.G. Calibration and performance assessment of an innovative high-temperature cavitometer. *Sensors and Actuators A: Physical* **2016**, *240*, 57–69.
40. Tzanakis, I.; Lebon, G.S.B.; Eskin, D.G.; Pericleous, K.A. Characterisation of the ultrasonic acoustic spectrum and pressure field in aluminium melt with an advanced cavitometer. *Journal of Materials Processing Technology* **2016**, *229*, 582–586.
41. Nastac, L. Mathematical Modeling of the Solidification Structure Evolution in the Presence of Ultrasonic Stirring. *Metallurgical and Materials Transactions B* **2011**, *42*, 1297–1305.
42. Nastac, L. Multiscale Modeling of Ingot Solidification Structure Controlled by Electromagnetic and Ultrasonic Stirring Technologies. In *CFD Modeling and Simulation in Materials Processing*; Nastac, L., Zhang, L., Thomas, B.G., Sabau, A., El-Kaddah, N., Powell, A.C., Combeau, H., Eds.; John Wiley & Sons, Inc.: Hoboken, NJ, USA, 2012; pp. 261–268 ISBN 978-1-118-36469-7.
43. Nastac, L. Numerical Modeling of Fluid Flow and Solidification Characteristics of Ultrasonically Processed A356 Alloys. *ISIJ International* **2014**, *54*, 1830–1835.
44. Song, S.; Zhou, X.; Li, L.; Ma, W. Numerical simulation and experimental validation of SiC nanoparticle distribution in magnesium melts during ultrasonic cavitation based processing of magnesium matrix nanocomposites. *Ultrasonics Sonochemistry* **2015**, *24*, 43–54.
45. Lebon, G.S.B.; Pericleous, K.; Tzanakis, I.; Eskin, D. A model of cavitation for the treatment of a moving liquid metal volume. *International Journal of Cast Metals Research* **2016**, *29*, 324–330.
46. Singhal, A.K.; Athavale, M.M.; Li, H.; Jiang, Y. Mathematical Basis and Validation of the Full Cavitation Model. *Journal of Fluids Engineering* **2002**, *124*, 617.
47. Plesset, M.S. The dynamics of cavitation bubbles. *Journal of Applied Mechanics* **1949**, *16*, 277–282.
48. Neppiras, E.A.; Noltingk, B.E. Cavitation Produced by Ultrasonics: Theoretical Conditions for the Onset of Cavitation. *Proceedings of the Physical Society. Section B* **1951**, *64*, 1032–1038.
49. Jasper, J.J. The Surface Tension of Pure Liquid Compounds. *Journal of Physical and Chemical Reference Data* **1972**, *1*, 841–1010.
50. Chen, Y.-J.; Hsu, W.-N.; Shih, J.-R. The Effect of Ultrasonic Treatment on Microstructural and Mechanical Properties of Cast Magnesium Alloys. *MATERIALS TRANSACTIONS* **2009**, *50*, 401–408.
51. Puga, H.; Barbosa, J.; Carneiro, V.H. The Role of Acoustic Pressure during Solidification of AlSi7Mg Alloy in Sand Mold Casting. *Metals* **2019**, *9*, 490.
52. Wang, S.; Kang, J.; Guo, Z.; Lee, T.L.; Zhang, X.; Wang, Q.; Deng, C.; Mi, J. In situ high speed imaging study and modelling of the fatigue fragmentation of dendritic structures in ultrasonic fields. *Acta Materialia* **2019**, *165*, 388–397.
53. Lebon, G.S.B.; Tzanakis, I.; Pericleous, K.A.; Eskin, D.G. Comparison between low-order and high-order acoustic pressure solvers for bubbly media computations. *Journal of Physics: Conference Series* **2015**, *656*, 012134.
54. Lebon, G.S.B.; Tzanakis, I.; Djambazov, G.; Pericleous, K.; Eskin, D.G. Numerical modelling of ultrasonic waves in a bubbly Newtonian liquid using a high-order acoustic cavitation model. *Ultrasonics Sonochemistry* **2017**, *37*, 660–668.
55. Manoylov, A.; Lebon, B.; Djambazov, G.; Pericleous, K. Coupling of Acoustic Cavitation with DEM-Based Particle Solvers for Modeling De-agglomeration of Particle Clusters in Liquid Metals. *Metallurgical and Materials Transactions A* **2017**, *48*, 5616–5627.

56. Lebon, G.S.B.; Kao, A.; Pericleous, K. The uncertain effect of cavitating bubbles on dendrites. In Proceedings of the Proceedings of the 6th Decennial International Conference on Solidification Processing; Old Windsor, UK, 2017; pp. 554–557.
57. Wang, Y.; Lebon, B.; Tzanakis, I.; Zhao, Y.; Wang, K.; Stella, J.; Poirier, T.; Darut, G.; Liao, H.; Planche, M.-P. Experimental and numerical investigation of cavitation-induced erosion in thermal sprayed single splats. *Ultrasonics Sonochemistry* **2019**, *52*, 336–343.
58. Tonry, C.E.H.; Djambazov, G.; Dybalska, A.; Bojarevics, V.; Griffiths, W.D.; Pericleous, K.A. Resonance from Contactless Ultrasound in Alloy Melts. In *Light Metals 2019*; Chesonis, C., Ed.; Springer International Publishing: Cham, 2019; pp. 1551–1559 ISBN 978-3-030-05863-0.
59. Djambazov, G.S.; Lai, C.-H.; Pericleous, K.A. Staggered-Mesh Computation for Aerodynamic Sound. *AIAA Journal* **2000**, *38*, 16–21.
60. Huang, H.; Shu, D.; Fu, Y.; Zhu, G.; Wang, D.; Dong, A.; Sun, B. Prediction of Cavitation Depth in an Al-Cu Alloy Melt with Bubble Characteristics Based on Synchrotron X-ray Radiography. *Metallurgical and Materials Transactions A* **2018**, *49*, 2193–2201.
61. Jamshidi, R.; Pohl, B.; Peuker, U.A.; Brenner, G. Numerical investigation of sonochemical reactors considering the effect of inhomogeneous bubble clouds on ultrasonic wave propagation. *Chemical Engineering Journal* **2012**, *189–190*, 364–375.
62. Chopra, K.; Prasada Rao, A.K. Ultrasonicated Direct Chill Clad Casting of Magnesium Alloy: A Computational Approach. *Transactions of the Indian Institute of Metals* **2019**.
63. Tzanakis, I.; Lebon, G.S.B.; Eskin, D.; Hyde, M.; Grant, P.S. Investigation of acoustic streaming and cavitation intensity in water as an analogue for liquid metal. In Proceedings of the Proceedings of the 10th International Symposium on Cavitation (CAV2018); Baltimore, Maryland, USA, 2018.
64. Wang, G.; Croaker, P.; Dargusch, M.; McGuckin, D.; StJohn, D. Evolution of the As-Cast Grain Microstructure of an Ultrasonically Treated Al-2Cu Alloy. *Advanced Engineering Materials* **2018**, *20*, 1800521.
65. Wang, G.; Wang, Q.; Balasubramani, N.; Qian, M.; Eskin, D.G.; Dargusch, M.S.; StJohn, D.H. The Role of Ultrasonically Induced Acoustic Streaming in Developing Fine Equiaxed Grains During the Solidification of an Al-2 Pct Cu Alloy. *Metallurgical and Materials Transactions A* **2019**.
66. Lee, Y.K.; Youn, J.I.; Kim, Y.J. Modeling of the Effect of Ultrasonic Frequency and Amplitude on Acoustic Streaming. In *Light Metals 2019*; Chesonis, C., Ed.; Springer International Publishing: Cham, 2019; pp. 1573–1578 ISBN 978-3-030-05863-0.
67. Lee, Y.K.; Youn, J.I.; Hwang, J.H.; Kim, J.H.; Kim, Y.J.; Lee, T.Y. Modeling of the effect of ultrasonic amplitude and frequency on acoustic streaming. *Japanese Journal of Applied Physics* **2019**, *58*, SGGD07.
68. Riedel, E.; Horn, I.; Stein, N.; Stein, H.; Bähr, R.; Scharf, S. Ultrasonic treatment: a clean technology that supports sustainability in casting processes. *Procedia CIRP* **2019**, *80*, 101–107.
69. Lebon, B.; Tzanakis, I.; Koulis Pericleous; Eskin, D.; Grant, P.S. Ultrasonic liquid metal processing: The essential role of cavitation bubbles in controlling acoustic streaming dataset 2019.
70. Vanhille, C.; Campos-Pozuelo, C. Nonlinear Ultrasonic Propagation in Bubbly Liquids: A Numerical Model. *Ultrasound in Medicine & Biology* **2008**, *34*, 792–808.
71. Vanhille, C.; Campos-Pozuelo, C. Nonlinear ultrasonic waves in bubbly liquids with nonhomogeneous bubble distribution: Numerical experiments. *Ultrasonics Sonochemistry* **2009**, *16*, 669–685.
72. Vanhille, C.; Campos-Pozuelo, C. Nonlinear ultrasonic standing waves: Two-dimensional simulations in bubbly liquids. *Ultrasonics Sonochemistry* **2011**, *18*, 679–682.
73. Lebon, B.; Salloum-Abou-Jaoude, G.; Eskin, D.; Tzanakis, I.; Koulis Pericleous; Phillipe Jarry Numerical modelling of acoustic streaming during the ultrasonic melt treatment of direct-chill (DC) casting dataset 2019.
74. Pericleous, K.A.; Bojarevics, V.; Djambazov, G.; Dybalska, A.; Griffiths, W.; Tonry, C. The Contactless Electromagnetic Sonotrode. In *Shape Casting*; Tiryakioğlu, M., Griffiths, W., Jolly, M., Eds.; Springer International Publishing: Cham, 2019; pp. 239–252 ISBN 978-3-030-06033-6.

